

# DF1400 and DF1471

**CHEMFILM® DF1400** and DF1471 are multilayer cast PTFE films produced using a proprietary process. The DF1400 has a non-conductive, fully fused, PTFE core coated with a conductive fluoropolymer formulation designed to be applied over jacketed wire and cable using standard tape-wrap equipment. The DF1471 is a fully conductive PTFE that is also available with a conductive FEP surface.

FEATURES	BENEFITS
<b>Cast Film</b>	<ul style="list-style-type: none"> <li>• Uniform tensile properties in both machine and traverse direction</li> <li>• Isotropic shrinkage as a function of temperature</li> </ul>
<b>Multilayer</b>	<ul style="list-style-type: none"> <li>• Polymers and additives may be added to individual layers to customize performance</li> </ul>
<b>Fluoropolymer</b>	<ul style="list-style-type: none"> <li>• Superior performance in a wide range of chemical, thermal and electrical environments</li> </ul>
<b>Slitting</b>	<ul style="list-style-type: none"> <li>• Available in slit widths to 1", supplied in pad rolls; minimum quantities apply</li> </ul>

## Typical Properties

	Method	Value
<b>MECHANICAL</b>		
Tensile Strength (psi)	ASTM D882-54T	4,000
Elongation (%)	ASTM D882-54T	400
Elastic Modulus (psi)	ASTM D882	60,000
Continuous Service Temp.		+500°F, -400°F +260°C, -188°C
<b>ELECTRICAL</b>		
Dielectric Constant, 60-10 <sup>8</sup> Hz	ASTM D150	12.0
Power/Dissipation	ASTM D150	0.036
Surface Resistivity	ASTM D257	Conductive
Volume Resistivity	ASTM D257	Conductive
Dielectric Strength (volts/mil)	ASTM D149	4,200 (DF1400 only)
Surface Arc Resistance	ASTM D495	0
<b>Product Number</b>	<b>DF1400</b>	<b>DF1471</b>
Available Gauge (mil)	2.5	1.0-4.0
Colors	Black	Black

Values shown are typical. Certified test reports for writing specifications are available.

The data listed herein fall within the normal range of product properties for the products described, but they should not be used to establish specification limits nor used alone as the basis of design. Saint-Gobain assumes no obligation or liability for any advice furnished by it or for results obtained with respect to these products. All such advice is provided gratis and Buyer assumes sole responsibility for results obtained in reliance thereon. Saint-Gobain warrants that the material itself does not infringe any United States patent, but no license is implied nor is any further warranty made.

**Saint-Gobain Performance Plastics Corporation**  
 14 McCaffrey Street  
 Hoosick Falls, NY 12090  
**Customer Service: (800) 962-2666**  
 Tel: (518) 686-7301  
 Fax: (800) 526-8479, (518) 686-4840  
[www.plastics.saint-gobain.com](http://www.plastics.saint-gobain.com)

**Limited Warranty:** For a period of 6 months from the date of first sale, Saint-Gobain Performance Plastics Corporation warrants this product(s) to be free from defects in manufacturing. Our only obligation will be to provide replacement product for any portion proving defective, or at our option, to refund the purchase price thereof. User assumes all other risks, if any, including the risk of injury, loss or damage, whether direct or consequential, arising out of the use, misuse, or inability to use this product(s). SAINT-GOBAIN PERFORMANCE PLASTICS DISCLAIMS ANY AND ALL OTHER WARRANTIES, EXPRESSED OR IMPLIED, INCLUDING THE IMPLIED WARRANTIES OF MERCHANTABILITY AND FITNESS FOR A PARTICULAR PURPOSE.

**NOTE:** Saint-Gobain Performance Plastics Corporation does not assume any responsibility or liability for any advice furnished by it, or for the performance or results of any installation or use of the product(s) or of any final product into which the product(s) may be incorporated by the purchaser and/or user. The purchaser and/or user should perform its own tests to determine the suitability and fitness of the product(s) for the particular purpose desired in any given situation.

CHEMFILM is a registered trademark.

©2002 Saint-Gobain Performance Plastics Corporation  
 AFF-1151-PDF-0902-SGCS