

Primary SG23

GLASS-PTFE

Saint-Gobain Performance Plastics CHR® Primary SG23 is fiberglass fabric impregnated with PTFE (polytetrafluoroethylene) dispersion and coated with high-temperature, pressure-sensitive acrylic adhesive.

Typical Properties

Product Number	SG23-03	SG23-05	SG23-06	SG23-10
Backing Material	PTFE-Coated Fiberglass Fabric	PTFE-Coated Fiberglass Fabric	PTFE-Coated Fiberglass Fabric	PTFE-Coated Fiberglass Fabric
Adhesive Type	Acrylic	Acrylic	Acrylic	Acrylic
Total Thickness (in.)	.0050	.0070	.0080	.0113
Backing Thickness (in.)	.0030	.0050	.0060	.0090
Adhesive Thickness (in.)	.0020	.0020	.0020	.0023
Adhesion to Steel (oz./in.)	60	70	75	70
Elongation (% at break)	<5	<5	<5	<5
Operating Temperature (°F)	-40 to 350	-40 to 350	-40 to 350	-40 to 350
Color	Natural	Natural	Natural	Natural

Values shown are typical. Certified test reports for writing specifications are available.

Applications—Saint-Gobain Performance Plastics Primary SG23 is frequently used by the packaging industry as a release surface on heat sealers, blister formation and form-fill-seal equipment. The durability and anti-stick properties of SG23 also make it an ideal material for the lining of guide rails, chutes and slides. The high temperature capabilities and non-stick properties of SG23 allow it to perform as an excellent release surface in the composite aircraft industry.

Features/Benefits—SG23 is a very durable and versatile product. The combination of PTFE, fiberglass and a high temperature acrylic adhesive allows SG23 to perform in continuous temperatures up to 350°F. SG23 is dimensionally stable and resistant to tears, punctures, abrasion and wear. It will not “cold flow” under heavy loads.

Availability—SG23 is available in 3, 5, 6, and 10 mil thicknesses and widths from 1/4" to 39" wide. Standard roll length is 18 or 36 yards long. SG23 is available with or without a liner.

Saint-Gobain Performance Plastics Corporation
14 McCaffrey Street
Hoosick Falls, NY 12090
Customer Service: (800) 962-2666
Tel: (518) 686-7301
Fax: (800) 526-8479, (518) 686-4840

www.fff.saint-gobain.com

Limited Warranty: For a period of 6 months from the date of first sale, Saint-Gobain Performance Plastics Corporation warrants this product(s) to be free from defects in manufacturing. Our only obligation will be to provide replacement product for any portion proving defective, or at our option, to refund the purchase price thereof. User assumes all other risks, if any, including the risk of injury, loss or damage, whether direct or consequential, arising out of the use, misuse, or inability to use this product(s). SAINT-GOBAIN PERFORMANCE PLASTICS DISCLAIMS ANY AND ALL OTHER WARRANTIES, EXPRESSED OR IMPLIED, INCLUDING THE IMPLIED WARRANTIES OF MERCHANTABILITY AND FITNESS FOR A PARTICULAR PURPOSE.

NOTE: Saint-Gobain Performance Plastics Corporation does not assume any responsibility or liability for any advice furnished by it, or for the performance or results of any installation or use of the product(s) or of any final product into which the product(s) may be incorporated by the purchaser and/or user. The purchaser and/or user should perform its own tests to determine the suitability and fitness of the product(s) for the particular purpose desired in any given situation.

CHR® is a registered trademark
©2004 Saint-Gobain Performance Plastics Corporation
AFF-1097-PDF-0304-SGCS