2253/2254 FILM-PTFE (SKIVED, HIGH-MODULUS)

Saint-Gobain Performance Plastics CHR® 2253 and 2254 are manufactured from modified PTFE (polytetrafluoroethylene) film coated with pressure-sensitive adhesive.

Typical Properties

Product Number	2253-2	2254-2
Backing Material	Film-PTFE	Film-PTFE
Adhesive Type	Acrylic	Silicone
Total Thickness (in.)	.0035	.0035
Backing Thickness (in.)	.0020	.0020
Adhesive Thickness (in.)	.0015	.0015
Adhesion to Steel (oz./in.)	30	35
Tensile Strength (lbs./in.)	30	30
Dielectric Strength (volts)	9500	9500
Elongation (% at break)	150	150
Operating Temperature (°F)	-40 to 350	-40 to 350
Color	Gray	Gray

Values shown are typical. Certified test reports for writing specifications are available.

Applications—The excellent conformability and release properties of the PTFE backing, along with the high temperature capability of the adhesive, make these tapes ideal for applications such as composite lay-up, roller wrapping, plate masking, heat sealing and other uses where costly clean up is a problem. The aerospace industry can also use these tapes in phase insulation for bundling end turns, spot bundling, anchor breakouts and to protect airframe wire harnesses.

Features/Benefits—Their most outstanding properties are its high dielectric and tensile strength, which make it an extremely durable insulation tape. The high temperature properties of the PTFE and adhesive allow it to perform in continuous temperatures up to 350°F or 500°F.

A high-modulus tape, they exhibit low elongation which enables it to be applied with automatic wrapping equipment. The other outstanding features include chemical inertness as well as low friction, anti-stick, non-toxic properties and clean release, making it the right material for numerous applications.

Availability—Factory stock is in master log form 36 yards long x 16" wide. Rolls can be slit in widths ranging from 1/2" to 16". Standard roll length is 36 yards. 2253-2 is available with or without a liner. 2254-2 is available with or without a liner, or etched topside for bondability.

Saint-Gobain Performance Plastics Corporation 14 McCaffrey Street Hoosick Falls, NY 12090 Customer Service: (800) 962-2666 Tel: (518) 686-7301 Fax: (800) 526-8479, (518) 686-4840

www.fff.saint-gobain.com

Limited Warranty: For a period of 6 months from the date of first sale. Saint-Gobain Performance Plastics Corporation warrants this product(s) to be free from defects in manufacturing. Our only obligation will be to provide replacement product for any portion proving defective, or at our option, to refund the purchase price thereof. User assumes all other risks, if any, including the risk of injury, loss or damage, whether direct or consequential, arising out of the use, misuse, or inability to use this product(s). SAINT-GOBAIN PERFORMANCE PLASTICS DISCLAIMS ANY AND ALL OTHER WARRANTIES, EXPRESSED OR IMPLIED, INCLUDING THE IMPLIED WARRANTIES OF MERCHANTABILITY AND FITNESS FOR A PARTICULAR PURPOSE.

NOTE: Saint-Gobain Performance Plastics Corporation does not assume any responsibility or liability for any advice furnished by it, or for the performance or results of any installation or use of the product(s) or of any final product into which the product(s) may be incorporated by the purchaser and/or user. The purchaser and/or user should perform its own tests to determine the suitability and fitness of the product(s) for the particular purpose desired in any given situation.

CHR® is a registered trademark ©2004 Saint-Gobain Performance Plastics Corporation AFF-1131-PDF-0304-SGCS

